Marine & Marine Anti-Aging BOAT PRIMER

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

Chlorinated rubber based primer for the Antifouling Marine&Marine Paint series.

PRODUCT FEATURES

- Prevents water penetration and protects steel structures from corrosion.
- Displays excellent adhesion to surfaces as well as to subsequent coatings of antifouling paint.

RECOMMENDED FOR

Priming of wood, polyester and metal surfaces both over and under water parts.

TECHNICAL SPECIFICATIONS

** The provided solids, viscosity and density data may vary depending on the color.*

Drying time		
Touch dry	4	h
Recoat	24	h
Full dry	24	h

** The specified drying time; lt is available in 23 C ambient temperature and 50 ± 2% relative humidity conditions.*
** Gel time, the amount of the mixture and varies depending on the ambient temperature.*

SURFACE

Polyester surfaces Wash with fresh water and wipe with Polisan or Polisel Cellulosic Thinner. After sanding, wipe the surface again with Polisan or Polisel Cellulosic Thinner and fresh water.

Surface should be clean and dry. Old primer and antiflouling paint on the surface should be removed.

Polisan Boya San. ve Tic. A.Ş.
Headquarters: İçerenköy Mah. Ali Nihat Tarlan Cad. No:86 Ataşehir 34752 İSTANBUL / **Phone:** +90 (0216) 578 56 00
Factory: Dilovası Organize Sanayi Bölgesi 1. Kısım Liman Cad. No:7 Dilovası / KOCAELI **Phone:** +90 (0262) 679 71 00
info@polisan.com.tr

Revision No : 05
Publish Date: 30.12.2023
Sample Text

Marine & Marine Anti-Aging BOAT PRIMER

TECHNICAL DATA SHEET

APPLICATION

Application Temperature	:	5 °C - 30 °C
Flash off (room temperature, min)	:	It is ready for use. Do not thin
Covered area (m^2/L)	:	10 (30 micron DFT)
Covered area (m^2/kg)	:	

For new wood surfaces apply 2 coats, metal surface apply 3 coats and previously painted old surfaces and polyester surfaces apply 1 coat Polimarin Underwater Primer. 24 hours should be allowed between coats.

Application Equipment

Brush
Roller

STORAGE and PACKAGING

Packaging	0.75 L 2.5 L 15 L
Storage Conditions	Store between 5-30°C in sealed packages away from direct sunlight. Keep the packaging closed when not in use. Protect from frost.
Shelf life	3 years

HEALTH AND SAFETY INFORMATION

Refer to the instructions specified in the harmfulness and precautionary statements on the product packaging.
Product of the safety data sheet should be treated by the rules.
Refer to the nearest health facility for unexpected health problems.

LEGAL NOTES

All the information and guidelines given in this technical bulletin was formed and developed through the experience in the laboratories of Polisan Kansai Paint, and was systematically collected by our field engineers. “Polisan Kansai Paint"has the right to make changes in the product where necessary, without notice. The information given above is valid for the product from the date of publication.It is the user's responsibility to verify the accuracy of the information. The product should be used based on the technical information form for the recommended purpose. It is the responsibility of the users to implement all measures for the fulfilment of the specified requirements.
The data in the technical information form is designed to give descriptions of the product performance, under specific test conditions. An important factor in product performance is the variables that may occur in the initial process which should be used as a general guide to the user. Any unauthorised use of this product not covered in the written guidelines, Polisan Kansai Paint will not be held legally responsible.
It is always the responsibility of the user to take all necessary precautions regarding specific requirements of the law set out in local and national legislation. Follow the rules of the safety information provided in the Safety Data Sheet regarding operating procedure of the product, protective equipment, storage, fire and first aid etc. Conditions regarding the use of this product after its end date has no warranty. We can not accept responsibility for products past their expiry date. Responsibility can not be accepted.

Please contact the Technical Service department for more detailed information about the product.

Polisan Boya San. ve Tic. A.Ş.
Headquarters: İçerenköy Mah. Ali Nihat Tarlan Cad. No:86 Ataşehir 34752 İSTANBUL / **Phone:** +90 (0216) 578 56 00
Factory: Dilovası Organize Sanayi Bölgesi 1. Kısım Liman Cad. No:7 Dilovası / KOCAELI **Phone:** +90 (0262) 679 71 00
info@polisan.com.tr

Revision No : 05
Publish Date: 30.12.2023
Sample Text