

PRIMERA GLOSSY

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

Alkyd based, glossy top coat synthetic paint

PRODUCT FEATURES

- Lead free
- Resistance to yellowing
- High glossy
- Good hiding power
- Easy aplication
- Good adhesion and perfectworking properties.

RECOMMENDED FOR

Primera Synthetic is applicable indoors and outdoors wooden, metal and plaster surface and It is used forland and marine vehicles.

TECHNICIAL SPECIFICATIONS

Drying time		
Touch dry	5-6	h
Recoat	1	day
Full dry	18	h

** The provided drying time data are available in 23 ºC ambient temperature and 50 ± 2 % relative humidity conditions.*

SURFACE

All surfaces must be clean, dry and free of dirt, chalk, grease, wax, rust and loose or peeling paint before painting.

Metal Surfaces For metal surface dirt, grease and oils should be cleaned. Primera Antipas Antirust Primer should be applied to the metal surface as a primer.

Other Surfaces On wooden surfaces; The knots are cleaned, any old paint is scraped off, sanded, and then primed with PRIMERA SYNTHETIC PRIMER.
Surfaces that need repair; It is puttyed with SUPER PASTE and primed with PRIMERA SYNTHETIC PRIMER. (It should not be applied directly on the surface primed with POLİZOLAN, the surface should be primed with PRİMERA SYNTHETIC PRIMER first.)

Polisan Kansai Boya San. ve Tic. A.Ş.
Headquarters: Hilltown Ofis, Aydınevler Mah. Siteler Yolu Cad. 28 No:1/A Küçükyalı-Maltepe, İstanbul / **Phone:+**90(216) 578 88 00
Factory: Dilovası Organize Sanayi Bölgesi 1. Kısım Liman Cad. No:7 Dilovası / KOCAELI **Phone:** +90 (0262) 679 71 00
Mail: info@kansaipolisan.com
www.kansaipolisan.com

Rev. no: 09
Publish Date: 05.12.2024
Sample Text



PRIMERA GLOSSY

TECHNICAL DATA SHEET

APPLICATION

It is recommended to be applied as two coats. One day should be allowed between the coats. Use Synthetic Thinner as thinner.

Application Temperature (°C)	: min +5 °C / max + 30 °C
Thinning Ratio (%)	: For Brush&Roller 10-15%, Spray 20%
Consumption (m ^{2} / L)	: 15-20 (for single coat)

Application Equipment

Brush	Applicable
Roller	Applicable
Spray	Applicable

TS CLASSIFICATION

TSE to 39 is appropriate and has the TSE.

POZ No.

04.551

STORAGE and PACKAGING

Packaging	0,25 L, 0,75 L, 2,5 L, 7,5 L, 15 L
Storage Conditions	Should be stored in closed packs without being exposed to direct sunlight. The ambient temperature while storage should be between 5-35 °C. Keep packs closed when not in use. Preserve against freezing.
Shelf life	3 years

HEALTH AND SAFETY INFORMATION

Refer to the instructions specified in the harmfulness and precautionary statements on the product packaging.
Product of the safety data sheet should be treated by the rules.
Refer to the nearest health facility for unexpected health problems.

LEGAL NOTES

All the information and guidelines given in this technical bulletin was formed and developed through the experience in the laboratories of PB, and was systematically collected by our field engineers. “Polisan Boya"has the right to make changes in the product where necessary, without notice. The information given above is valid for the product from the date of publication.It is the user's responsibility to verify the accuracy of the information. The product should be used based on the technical information form for the recommended purpose. It is the responsibility of the users to implement all measures for the fulfilment of the specified requirements. The data in the technical information form is designed to give descriptions of the product performance, under specific test conditions. An important factor in product performance is the variables that may occur in the initial process which should be used as a general guide to the user. Any unauthorised use of this product not covered in the written guidelines, PB will not be held legally responsible. It is always the responsibility of the user to take all necessary precautions regarding specific requirements of the law set out in local and national legislation. Follow the rules of the safety information provided in the Safety Data Sheet regarding operating procedure of the product, protective equipment, storage, fire and first aid etc. Conditions regarding the use of this product after its end date has no warranty. We can not accept responsibility for products past their expiry date. Responsibility can not be accepted.

Please contact the Technical Service department for more detailed information about the product.

Polisan Kansai Boya San. ve Tic. A.Ş.
Headquarters: Hilltown Ofis, Aydınevler Mah. Siteler Yolu Cad. 28 No:1/A Küçükyalı-Maltepe, İstanbul / **Phone:+**90(216) 578 88 00
Factory: Dilovası Organize Sanayi Bölgesi 1. Kısım Liman Cad. No:7 Dilovası / KOCAELI **Phone:** +90 (0262) 679 71 00
Mail: info@kansaipolisan.com
www.kansaipolisan.com

Rev. no: 09
Publish Date: 05.12.2024
Sample Text